



# Rekoat 84

Offset printing paper with high whiteness based on 100% performance fibre

| TYPICAL END USES   |           | BENEFITS   |            |           | FINISH           |           | PRINTING METHODS                            |             |
|--|-----------|--|------------|-----------|------------------|-----------|---|-------------|
| Brochures, leaflets, reports, catalogues, calendar, school and writing books |           | High brightness<br>Good opacity<br>Treated for ink fastness* |            |           | silk mat surface |           | Heatset<br>Offset<br>Digital<br>Letterpress |             |
| <b>Substance</b>   | ISO 536   | <b>g/m<sup>2</sup></b>                                       | <b>60*</b> | <b>70</b> | <b>80</b>        | <b>90</b> | <b>100</b>                                  | <b>115*</b> |
| <b>Brightness</b>  | ISO 2470  | %  | 84         | 84        | 84               | 84        | 84  | 84          |
| <b>Opacity</b>   | ISO 2471  | %  | 94         | 96        | 98               | 98        | 98  | 98          |
| <b>Gloss (Gardner 75°)</b>   | Tappi 480 | %  | 20         | 20        | 20               | 20        | 20  | 20          |
| <b>Smoothness Bekk</b>   | DIN 53107 | sec  | 250        | 200       | 200              | 200       | 200   | 200         |
| <b>Bulk</b>  | ISO 534   | cm <sup>3</sup> /g   | 1,00       | 1,00      | 1,00             | 1,00      | 1,00  | 1,00        |

\*on demand

| REEL SPECIFICATIONS   | ENVIRONMENT   | CERTIFICATES   |
|---|---|--|
| Cores: 70 mm, 76 mm, 150 mm<br>Trimmed width: 3780 mm<br>Width: min. 340 mm, max. 2860 mm<br>Diameters: min. 1000 mm, max 1250 mm<br>Max. Weight: 3900 kg | 100 % sustainable fibers and sources<br>No chlorine bleaching in production process<br>Recyclable paper<br>Recyclable packaging materials | FSC®<br>PEFC™<br>Blauer Engel RAL-UZ 72*<br>EU Ecolabel* |

Available in sheet formats upon request

## STORAGE AND HANDLING

- Store the paper in a humidity and temperature controlled area at 50 % relative humidity and room temperature between 19 °C and 23 °C.
- If the paper is stored in non - air conditioned warehouse, it is absolutely necessary to allow a stabilization period in the print room.
- Open the protective wrapping at the moment of use.

Kübler & Niethammer Papierfabrik Kriebstein AG  
Bauhofstraße 1  
OT Kriebethal, 09648 Kriebstein  
Tel +49 (0) 34327 97-50  
info@k-n-paper.de